



US009510932B2

(12) **United States Patent**  
**Kumta et al.**

(10) **Patent No.:** US 9,510,932 B2  
(45) **Date of Patent:** Dec. 6, 2016

(54) **BIODEGRADABLE METAL ALLOYS**

(71) Applicant: **UNIVERSITY OF PITTSBURGH-OF THE COMMONWEALTH SYSTEM OF HIGHER EDUCATION, Pittsburgh, PA (US)**

(72) Inventors: **Prashant N. Kumta**, Pittsburgh, PA (US); **Da-Tren Chou**, Pittsburgh, PA (US); **Dacho Hong**, Pittsburgh, PA (US); **Partha Saha**, Pittsburgh, PA (US)

(73) Assignee: **University of Pittsburgh-Of the Commonwealth System of Higher Education**, Pittsburgh, PA (US)

(\*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 0 days.

(21) Appl. No.: **14/349,564**

(22) PCT Filed: **Oct. 5, 2012**

(86) PCT No.: **PCT/US2012/058939**

§ 371 (c)(1),  
(2) Date: **Apr. 3, 2014**

(87) PCT Pub. No.: **WO2013/052791**

PCT Pub. Date: **Apr. 11, 2013**

(65) **Prior Publication Data**

US 2014/0248288 A1 Sep. 4, 2014

**Related U.S. Application Data**

(60) Provisional application No. 61/544,127, filed on Oct. 6, 2011.

(51) **Int. Cl.**

**A61F 2/02** (2006.01)  
**C22C 23/00** (2006.01)  
**C22C 23/04** (2006.01)  
**C22C 23/06** (2006.01)  
**C22C 1/02** (2006.01)  
**C22F 1/06** (2006.01)  
**A61L 27/04** (2006.01)  
**A61L 27/58** (2006.01)  
**A61K 31/397** (2006.01)  
**A61K 31/7036** (2006.01)

(52) **U.S. Cl.**

CPC ..... **A61F 2/02** (2013.01); **A61K 31/397** (2013.01); **A61K 31/7036** (2013.01); **A61L 27/047** (2013.01); **A61L 27/58** (2013.01); **C22C 1/02** (2013.01); **C22C 23/00** (2013.01); **C22C 23/04** (2013.01); **C22C 23/06** (2013.01); **C22F 1/06** (2013.01)

(58) **Field of Classification Search**

CPC ..... A61F 2/02; C22C 23/00; C22C 23/04; C22C 23/06; C22C 1/02; A61K 31/397; A61K 31/7036; A61K 33/24; A61K 33/30; A61K 33/32; A61K 33/38; A61L 27/047; A61L 27/58; C22F 1/06

See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

8,293,031	B2	10/2012	Gerold et al.
8,435,281	B2	5/2013	Weber
2007/0227629	A1	10/2007	Gerold et al.
2008/0031765	A1	2/2008	Gerold et al.
2008/0035350	A1	2/2008	Zberg et al.
2009/0081313	A1	3/2009	Aghion et al.
2011/0192500	A1	8/2011	Uggowitz et al.
2013/0144290	A1	6/2013	Schiffl et al.
2013/0195714	A1	8/2013	Lyon

FOREIGN PATENT DOCUMENTS

JP	08027533	1/1996
KR	1020080027202	3/2008
KR	1020110065390 A	6/2011

OTHER PUBLICATIONS

Huinan Liu, "Nanotechnology Enabled in situ Sensors for Monitoring Health; Chapter 6: Biodegradable Metals and Responsive Biosensors for Musculoskeletal Applications" 2010, Springer Science & Business Media, vol. 68 of The new synthase historical library, p. 115-137.\*

Won-Wook Park et al., "Microstructural change and precipitation hardening in melt-spun MG-X-Ca alloys", Science and Technology of Advanced Materials (2001), 2, 73-78.\*

\* cited by examiner

*Primary Examiner* — Sue Liu

*Assistant Examiner* — Nathan W Schlientz

(74) *Attorney, Agent, or Firm* — Eckert Seamans Cherin & Melloyy, LLC; Carol A. Marmo

(57) **ABSTRACT**

The invention relates to biodegradable, metal alloy-containing compositions, methods for their preparation and applications for their use. The compositions include magnesium and other components, such as yttrium, calcium, silver, cerium, and zirconium; or zinc, silver, cerium, and zirconium; or aluminum, zinc, calcium, manganese, silver, yttrium; or strontium, calcium, zinc. The compositions are prepared by vacuum induction/crucible melting together the components and casting the melted mixture in a preheated mild steel/copper mold. In certain embodiments, the compositions of the invention are particularly useful for forming medical devices for implantation into a body of a patient.

**14 Claims, No Drawings**